

Table I
Identification of Achievable Performance Standards
Source Category: Pleasure Craft Coating Operations

Regulated Component	Pollutant	Rule/Measure/Date							
		SCAQMD 1106-1 6/13/97							
		Performance Standard							
High Gloss	VOC	420 g/l							
Extreme High Gloss	VOC	490 g/l							
Pretreatment Wash Primers	VOC	780 g/l							
Finish Primer/Surfacer	VOC	420 g/l							
High Build Primer Surfacer	VOC	340 g/l							
Teak Primer	VOC	775 g/l							
Antifoulant Coatings	VOC								
Aluminum Substrate		560 g/l							
Other Substrates		150 g/l							
Clear Wood Finishes	VOC								
Sealers		550 g/l							
Varnishes		490 g/l							
Others		420 g/l							

Table I
Identification of Achievable Performance Standards
Source Category: Pleasure Craft Coating Operations

Regulated Component	Pollutant	Rule/Measure/Date							
		SCAQMD 1106-1 6/13/97							
		Performance Standard							
Application Method		hand application, HVLV, or equivalent, approved method							
Cleaning Equipment		facilities must use wipe cleaning, spray bottles, enclosed cleaning device, or approved clean-up equipment							
Surface Preparation Solvents		70 g/l							
Recordkeeping		<ul style="list-style-type: none"> - application method and substrate type - amount of coating and solvents used - VOC content of coatings and solvents - vapor pressure of coatings and solvents - oven temperature 							

Table I
Identification of Achievable Performance Standards
Source Category: Pleasure Craft Coating Operations

Regulated Component	Pollutant	Rule/Measure/Date									
		SCAQMD 1106-1 6/13/97									
		Performance Standard									
Solvent Loss Minimization			use closed containers for storage and disposal of cleaning rags and close solvent-containing containers when not in use								

S:\DRAT\WEBDOCS\PLEAS1.WP6